



	<b>Experiment title:</b> Temperature dependent magnetic EXAFS at Tb L-edges	<b>Experiment number:</b> HE-756
<b>Beamline:</b> ID 12 A	<b>Date of experiment:</b> from: 26.4.2000 to: 1.5.2000	<b>Date of report:</b> 10.2.2001
<b>Shifts:</b> 18	<b>Local contact(s):</b> A. Rogalev	<i>Received at ESRF:</i>

**Names and affiliations of applicants** (\* indicates experimentalists):


Heiko Wende\*, Andreas Scherz\*, Gustavo Ceballos\*, Fabrice Wilhelm, Panagiotis Pouloupoulos, Klaus Baberschke  
*Institut für Experimentalphysik, Freie Universität Berlin, Arnimallee 14, D-14195 Berlin*

Thomas A. Lograsso, Deborah L. Schlager  
*Ames Laboratory, Iowa State University, Ames, Iowa USA 50011*

**Report:**

The magnetic EXAFS (MEXAFS) data were recorded using a Tb single crystal. The measurements in the extended energy range of the L<sub>3</sub>-edge allowed for a suitable energy range for the EXAFS analysis of  $\Delta E=400$  eV. This value corresponds to a maximum possible photoelectron wavenumber of  $k_{\max}=10 \text{ \AA}^{-1}$ . To keep the degree of circular polarization constant in this extended energy range together with a high photon flux, the gap-scanning technique was used. This reliable technique worked very satisfactorily in our entire beamtime. The data were measured at four temperatures: 10 K, 150 K, 225 K and 250 K. These temperatures were chosen for the following reasons: at 10 K the dynamic disorder due to lattice vibrations and due to spin-fluctuations are reduced to a minimum value. The higher temperatures were selected to be around the Curie temperature of Tb which is  $T_C=221$  K. Hence a slightly higher temperature of 225 K was used to investigate the influence of critical fluctuations close to  $T_C$ . A still open question is the degree of magnetic order of the system on a local scale above the Curie temperature. Therefore the highest temperature was set to 250 K. The experimental results for the difference  $\Delta\mu(E)$  of the x-ray absorption coefficients for right ( $\mu^+(E)$ ) and left ( $\mu^-(E)$ ) circularly polarized x-rays are given in Fig. 1. Clear MEXAFS wiggles can be detected at 10 K up to a photon energy of 7925 eV. The wiggles fade out starting from the higher photon energies with increasing temperature. This is due to the exponential form of the EXAFS Debye-Waller factor  $\exp(-2\sigma^2(T)k^2)$  leading to a stronger damping at higher k-values corresponding to higher photon energies. Furthermore, there is a reduction due the decrease of the magnetization  $M(T)$  versus temperature. But still at 250 K a clear oscillatory fine structure can be identified. This indicates that there is still magnetic ordering on a local scale in applied

field of 2.7 T. For a more detailed analysis of the local magnetic ordering the individual scattering paths must be investigated in the Fourier transform. But before Fourier transforming the data, contributions due to magnetic multi-electron excitations (MMEs) have to be removed.



**Fig. 1:** Difference of the x-ray absorption coefficients for right ( $\mu^+(E)$ ) and left ( $\mu^-(E)$ ) circularly polarized x-rays. Clear MEXAFS wiggles can be detected which get strongly damped at higher photon energies with increasing temperature.

These MMEs are found at a photon energy of about 7670 as marked in Fig. 1. By comparison to *ab initio* calculations using the FEFF code, the origin of the peak-like structure can be identified to be the MME and not the single-electron scattering effect. This code calculates the x-ray absorption coefficients in a single-electron multiple-scattering approach. By means of comparison of the calculation with the experimental data a clear peak-like-structure can be identified. It turned out that the multi-electron excitations have stronger effects on the Fourier transform for the Tb MEXAFS data than it was found in our earlier MEXAFS investigations for Gd [1,2]. We are now working on a reliable subtraction procedure. Then the questions raised above will be analyzed using the Fourier transformed data.

- [1] H. Wende, F. Wilhelm, P. Pouloupoulos, K. Baberschke, J.W. Freeland, Y.U. Idzerda, A. Rogalev, D.L. Schlagel, T.A. Lograsso and D. Arvanitis, AIP Conference Proceedings vol. **514**, eds. M. Benfatto, C.R. Natoli and E. Pace, Melville (New York), (2000) pp. 140-147.
- [2] H. Wende, F. Wilhelm, P. Pouloupoulos, A. Rogalev, D.L. Schlagel, T.A. Lograsso and K. Baberschke, J. Synchr. Rad. (in press).